

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09H 5/00, A61K 9/48	A2	(11) International Publication Number: WO 96/14365 (43) International Publication Date: 17 May 1996 (17.05.96)
(21) International Application Number: PCT/US95/13950 (22) International Filing Date: 31 October 1995 (31.10.95) (30) Priority Data: 08/334,974 7 November 1994 (07.11.94) US (71) Applicant: WARNER-LAMBERT COMPANY [US/US]; 201 Tabor Road, Morris Plains, NJ 07950 (US). (72) Inventors: CADE, Dominique; 11, rue des Americains, F-68000 Colmar (FR). MADIT, Nicolas; 51, avenue du Marechal- Juin, F-68100 Mulhouse (FR). (74) Agents: RYAN, M., Andrea; Warner-Lambert Company, 201 Tabor Road, Morris Plains, NJ 07950 (US) et al.		(81) Designated States: CA, CN, JP, KR, MX, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: PROCESS FOR STABILIZING GELATIN PRODUCTS (57) Abstract Process for the manufacturing of gelatin products with improved stability against storage under hot and humid conditions and/or aldehydes characterized in that at least one additive, preferred glutamic acid, tryptophan, or nitrilotrismethylene phosphonic acid or a mixture thereof is incorporated into the gelatin before forming the final product as usual as well as the gelatin compositions used and the products obtained by the process.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Larvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Process for Stabilizing Gelatin Products

FIELD OF THE INVENTION

This invention relates to a process for the enhancement of the stability of gelatin products against higher storage temperatures, humidity and/or chemically influenced crosslinking, as well as suitable gelatin compositions and their use in capsule manufacturing or as coating or binding agents of tablets, casing materials and so on.

DESCRIPTION OF THE PRIOR ART

Gelatin is widely used in the pharmaceutical industry as well as in the health food supplement market to manufacture capsules as containers or as coating agents for the capsules or other dosage forms, or as adjuvants or excipients in pharmaceutical preparations like tablets. A primary objective of these dosage forms is to have a good disintegration after being administrated in order to enable a fast dissolution of the active substances in the appropriate digestive organ. Any delay of the disintegration would consequently retard or even reduce the effect of the drug. Consequently, this disintegration characteristic has to remain unchanged over time when finished products are stored prior to use. Extensive dissolution stability testing has been conducted to assess this stability.

Unfortunately, as has been widely described in the literature, the risk for the gelatin product to exhibit a delay in disintegration over time is high. A primary cause of the problem, exposure to certain aldehydes contained in the capsules content at the initial stage or originating from the decomposition of the drug or one of the excipients over time, has been reported in many references as a cause. The mechanism of this chemical interaction named "crosslinking" has been well understood as action of the aldehyde on the free amino groups of the amino acids and especially the

lysine and arginine (G. Digenis & al, to be published in J. of Pharm. Sci.). It has also been used further in the sense that overcrosslinking of the gelatin would make it totally insoluble and inappropriate for an enteric dosage form (G. Gutierrez, FR-8201127).

Various patents have been published which deal with this issue. The resistance to crosslinking by formaldehyde can be obtained by chemically modifying the gelatin (succinylated gelatin: Toyo Jozo Co, JP 61/186315 Nippon Elanco Co, JP-61/186314), by adding ions in it (Sanofi, FR-8708828) or silicones (R.P. Scherer, FR-2346/69) or peptides (NITTA, EP-0 335 982).

Another procedure to protect gelatin from crosslinking is to include in the formulation of the drug a formaldehyde scavenger (Teikoku Hormone Mfg Co, JP-168874/1989 and Lion Corporation EP-0 242 855).

Some literature references have also reported that exposure or storage to/under hot and humid conditions is another reason for the delay in the disintegration of gelatin products. These conditions were reported in a temperature range of 25 to 55°C and a humidity range of 40% to 90% relative humidity. This appears to be very important for most of the pharmaceutical applications of the gelatin where a stability is requested for storage at 40°C with 75% RH over 3 to 6 months without significant delay in drug dissolution.

This phenomenon was described extensively in the literature, but no proposal has been made to explain the mechanism of the chemical reactions involved in responsible for the poorer dissolution performance of the gelatin: H.W. GOUDA & al., Intl. Jour. Pharmaceutics, 18, 1984, 213-215; S.A. KHALIL & al., Pharmazie, 29 H1, 1974, 36-37; T.C. HAHL & al., Drug Dvpt Industr. Pharmacy, 17 (7), 1991, 1001-1016; M.

DEY & al., Pharmaceutical Res., 10 (9), 1993, 1295-1300; K.S. MURPHY & al., Pharm. Techno., March, 1989, 74-82. In the state of the art, no method is known for increasing the resistance of the gelatin to storage at hot and humid conditions as described before.

SUMMARY OF THE INVENTION

The present invention relates to a process for the manufacturing of gelatin products which have improved stability against storage under hot and humid conditions and/or aldehydes in order to improve the dissolution of the gelatin products comprising incorporating additives into the gelatin solution and forming the final product as usual. A further aspect of the invention is the gelatin compositions used for the gelatin products prepared by the process.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

The gelatin to be used with the present invention may be from acid processed pork skin known as A gelatins, from lime processed bones known as B gelatins, from calf skin known as C gelatins, acid processed bones known as AB gelatins or from a combination of two or more of these gelatins.

The additives are selected from the group consisting of ammonium sulfate, ammonium hydrogen sulfate, ammonium hydrogencarbonate, ammonium phosphate, ammonium hydrogenphosphate, ammonium dihydrogenphosphate, ammonium thiocyanate, sodium sulfate, sodium chloride, potassium sulfate, potassium chloride, lithium sulfate, lithium chloride, calcium sulfate, calcium chloride, magnesium sulfate, magnesium chloride, iron (II) sulfate, iron (II) chloride, iron (III) sulfate, iron (III) chloride, manganese (II) sulfate, manganese (II) chloride, glutamic acid, aspartic acid, asparagine, lysine, tryptophane, arginine, guanidine, urea, citric acid, ascorbic acid, ethylenediamine tetraacetate, nitrilotrismethylene phosphonic acid.

The amount of additives is up to 25%, preferably 0.1 to 10% by weight of the dry gelatin. Each additive can be added alone or in combination with one or more additive.

Two types of storage conditions were studied:

- 5 1) Hot and humid conditions: temperature varied
 between 20 and 55°C and humidity between 40% and
 95% RH.
- 2) Formaldehyde:
- 10 a. Capsules were filled with lactose contaminated by
 formaldehyde with levels varying between 0-200 ppm,
 preferably between 1 and 60 ppm. These capsules were
 either stored in closed bottles at 50°C up to 2 months
 or in the open at hot and humid conditions up to 6
 months.
- 15 b. Gelatin films were stored in lactose powder
 contaminated by formaldehyde with level between 0 and
 200 ppm, preferably between 1 and 50 ppm. Films are
 dipped in the contaminated lactose powder in a closed
 plastic box and kept at 50°C up to 1 month.

20 Dissolution measurements:

 The dissolution measurements were made with the
 apparatus described in USP XXII, method II (paddle 50 rpm).
 The medium was demineralized water at 37°C ± 0.5°C and two
 procedures were used one for the capsules and one for the
25 gelatin films. The samples are added in the media in a
 special sinker which prevents them from floating.

1. Capsule dissolution:

The capsules are previously stored under one or both of the storage conditions described before. The capsules were filled with Acetaminophen and dissolved in water at 37°C under agitation (paddle 50 rpm). The percentage of dissolved Acetaminophen is determined by UV spectrophotometry at 300 nm. The required level of dissolved Acetaminophen is higher than 80% at 45 min.

2. Gelatin film dissolution

Films of gelatin are casted on glass plates. These films are stored at one or both of the conditions described before. The films are then added in demineralized water at 37°C under agitation (paddle 50 rpm) and the percentage of dissolution is determined by UV spectrophotometry at 217 nm. Uncrosslinked films have a dissolution of more than 90% at 6 min.

The following examples will demonstrate how the addition of inventive compounds increases the resistance of gelatins to crosslinking by hot and humid storage and/or formaldehyde.

Example 1:

We studied the effect of addition of ammonium sulfate (2% w/w of gelatin) on the resistance of gelatin to formaldehyde crosslinking. Gelatins type a 240 and type B 200 or two different suppliers with two batches each were studies. The gelatin films were casted from a 30% gelatin solution containing 2% w/w of ammonium sulfate ($(\text{NH}_4)_2\text{SO}_4$) and without additives (Reference). Films were dried at room conditions for 24 hours and dissolution samples were prepared and stored in formaldehyde contaminated lactose powder (at 5 ppm formaldehyde at 50°C for 1 week).

The dissolution results (%) are summarized in table 1 in comparison to mean values of 4 batches stored for 1 week at room conditions.

Table 1

5

Gelatin	Supplier	Batch	Reference		$(\text{NH}_4)_2\text{SO}_4$	
			3 min	6 min	3 min	6 min
A 240	A	1	10%	35%	80%	96%
		2	7%	46%	86%	98%
	B	1	11%	60%	76%	98%
		2	20%	70%	60%	96%
	Mean value for 4 batches		81%	97%	74%	93%

10

Table 1 demonstrates a very impressive resistance to formaldehyde crosslinking. Gelatin films with ammonium sulfate have practically the same dissolution results at 3 and 6 min as gelatin films stored at room conditions (mean values for 4 batches). A dramatic decrease in dissolution is noted for films without additives (Reference), especially for dissolution measures at 3 min.

Example 2:

15

The effect of addition of nitrilotrismethylene phosphonic acid (AMP, Masquol P320) on the dissolution of gelatin films stored in presence of formaldehyde is studied. The films were prepared by casting a gelatin solution (30% w/w water) containing Masquol P320 (1% w/w gelatin on glass

20

plate and drying at room conditions for 24 hours. The dissolution samples were then prepared and stored dipped in formaldehyde contaminated lactose in a closed plastic box for 1 week at 50°C prior to dissolution measurements.

The dissolution results are shown in the following table

2.

Table 2

Gelatin	AMP	Dissolution				
		3 min	6 min	9 min	12 min	15 min
A 240	0%	0%	3%	10%	16%	21%
	1%	3%	15%	26%	41%	52%
B 200	0%	8%	42%	70%	84%	87%
	1%	8%	77%	89%	93%	94%

Here the beneficial effect of the addition of an additive, Masquol P320, on the resistance of gelatin films to formaldehyde crosslinking is clearly demonstrated.

Effectively, a significant increase in the dissolution of gelatin films was observed for both A 240 films (+150% at 15 min) and B 200 films (+85% at 6 min).

Example 3:

Gelatin films with amino acids as additives were prepared and stored at hot and humid conditions prior to dissolution measurements. Gelatin films were casted from 30% w/w solution containing either 1% Tryptophan or 1% Glutamic acid. Gelatin films of A 240 and of B 200 were prepared. Films were dried at room conditions for 24 hours prior to sample preparation. The samples were stored at 50°C and 80% RH for 3 (A240) or 4 months (B 200) prior to dissolution measurements. The results are shown in table 3 in comparison with gelatin without additives stored at room temperature (Ref.).

Table 3
(Storage 50°C/80% RH for 3 (A 240) and 4 months (B 200))

Gelatine	Additive	Dissolution (%) after minutes				
		3	6	9	12	15
A 240	0%	6%	8%	14%	36%	67%
	1% Glu	6%	50%	92%	99%	100%
	1% Trp	10%	87%	97%	99%	100%
B 200	0%	3%	76%	92%	98%	98%
	1% Glu	54%	92%	97%	99%	100%
	1% Trp	59%	97%	100%	100%	100%
A 240	0% Ref.	72%	96%	99%	100%	100%
B 200	0% Ref.	96%	100%	100%	100%	100%

The dissolution results, compared with reference tests, demonstrate that the addition of amino acids, specifically Glutamic acid and Tryptophan at 1% level (in respect of dry gelatin) increases the dissolution of gelatin films especially at 3 min for B 200 and 9 min for A 240 gelatins.

In both cases, we reached the total dissolution of gelatin films (100% dissolution) more rapidly with additives than with reference films stored at the same conditions.

Example 4:

Gelatin films with salts or organic compounds were prepared as in example 3. The following products were added at 1% level compared to dry gelatin weight: urea and Masquol P320 (AMP).

The dissolution measurements were performed as for example 3 and results are summarized in following table 4:

Table 4

Gelatine	Additive	Dissolution (%) after minutes				
		3	6	9	12	15
A 240	0%	6%	8%	14%	36%	67%
	1% Glu	10%	92%	99%	100%	100%
	1% AMP	94%	97%	100%	100%	100%
B 200	0%	3%	76%	92%	98%	98%
	1% Urea	79%	97%	99%	100%	100%
	1% AMP	77%	94%	99%	100%	100%
A 240	0% Ref.	72%	96%	99%	100%	100%
B 200	0% Ref.	96%	100%	100%	100%	100%

The addition organic compounds (Urea, Masquol P320) increased significantly the dissolution of gelatin films of both type A 240 and B 200.

For A 240 the 100% dissolution is obtained at about 6 min compared to only 8% dissolution for gelatin films without additives. This result is comparable to reference films (Ref.) stored at normal conditions. The dissolution is higher than 75% for B 200 gelatin after only 3 min (3% for B 200 films without additives). These results are comparable to reference B 200 films (Ref.) stored at normal conditions.

As demonstrated from these examples, the incorporation of selected additives into the gelatin films increases the resistance of gelatin films and capsules to crosslinking in presence of aldehydes or when stored in hot and humid conditions.

Example 5:

The dissolution of capsules containing additives and filled with lactose contaminated by formaldehyde (5ppm or 20

ppm) and stored at 50°C in closed bottles for 1 or 2 months was studied. The results are expressed as the level of dissolution of acetaminophen filled in the capsules and measured according to the USP XXII Method 2.

5

Table 5

Test	Additive	Dissolution (%) after minutes				
		15	30	45	60	75
A	0%	12%	40	57%	71%	79%
	2% (I)	39%	68%	87%	95%	97%
B	0%	24%	50%	66%	78%	88%
	2% (I)	40%	72%	90%	98%	100%
	1% (II)	39%	79%	95%	100%	100%
C	0%	43%	79%	94%	98%	99%

10

Test A: Storage 4 weeks at 50°C, 20 ppm formaldehyde

Test B: Storage 2 months at 50°C, 5 ppm formaldehyde

Test C: Reference storage at room conditions

Additive (I): Ammoniumsulfate

Additive (II): Aspartic acid

15

The dissolution of capsules containing additives is better than the reference one. This dissolution is equal to the dissolution of a standard capsules stored at room conditions.

20

While there have been described what are presently believed to be the preferred embodiments of the invention, those skilled in the art will realize that various changes and modifications may be made to the invention without departing from the spirit of the invention, and it is intended to claim all such changes and modifications as fall within the scope of the invention.

We claim:

1. A process for the manufacturing of gelatin products with improved stability for storage under hot and humid conditions and/or aldehydes characterized in that at least one additive selected from the group consisting essentially of ammonium sulfate, ammonium hydrogen sulfate, ammonium hydrogencarbonate, ammonium phosphate, ammonium hydrogenphosphate, ammonium dihydrogenphosphate, ammonium thiocyanate, sodium sulfate, sodium chloride, potassium sulfate, potassium chloride, lithium sulfate, lithium chloride, calcium sulfate, calcium chloride, magnesium sulfate, magnesium chloride, iron (II) sulfate, iron (II) chloride, iron (III) sulfate, iron (III) chloride, manganese (II) sulfate, manganese (II) chloride, glutamic acid, aspartic acid, asparagine, lysine, tryptophane, arginine, guanidine, urea, citric acid, ascorbic acid, ethylenediamine tetraacetate, nitrilotrismethylene phosphonic acid or a mixture thereof is incorporated into the gelatin before forming a final gelatin product.
2. A process according to claim 1 wherein the additive or the mixture of additives is incorporated in the gelatin in an amount of up to 25%.
3. A process according to claim 2, wherein the additive or the mixture of additives is incorporated in the gelatin in an amount of from about 0.1 to about 10% by weight of the dry gelatin.
4. A process according to claim 3 for the manufacture of gelatin films, capsules, casings or coatings.
5. A gelatin composition containing additives with improved stability for storage under hot and humid conditions and/or aldehydes, comprising at least one additive

selected from the group consist. } essentially of
ammonium sulfate, ammonium hydrogen sulfate, ammonium
hydrogencarbonate, ammonium phosphate, ammonium
hydrogenphosphate, ammonium dihydrogenphosphate,
5 ammonium thiocyanate, sodium sulfate, sodium chloride,
potassium sulfate, potassium chloride, lithium sulfate,
lithium chloride, calcium sulfate, calcium chloride,
magnesium sulfate, magnesium chloride, iron (II)
sulfate, iron (II) chloride, iron (III) sulfate, iron
10 (III) chloride, manganese (II) sulfate, manganese (II)
chloride, glutamic acid, aspartic acid, asparagine,
lysine, tryptophane, arginine, guanidine, urea, citric
acid, ascorbic acid, ethylenediamine tetraacetate,
nitrilotrismethylene phosphonic acid or a mixture
15 thereof.

6. A gelatin product prepared from compositions with
improved stability for storage under hot and humid
conditions and/or aldehydes comprising at least one
additive selected from the group consisting essentially
20 of ammonium sulfate, ammonium hydrogen sulfate, ammonium
hydrogencarbonate, ammonium phosphate, ammonium
hydrogenphosphate, ammonium dihydrogenphosphate,
ammonium thiocyanate, sodium sulfate, sodium chloride,
potassium sulfate, potassium chloride, lithium sulfate,
25 lithium chloride, calcium sulfate, calcium chloride,
magnesium sulfate, magnesium chloride, iron (II)
sulfate, iron (II) chloride, iron (III) sulfate, iron
(III) chloride, manganese (II) sulfate, manganese (II)
chloride, glutamic acid, aspartic acid, asparagine,
30 lysine, tryptophane, arginine, guanidine, urea, citric
acid, ascorbic acid, ethylenediamine tetraacetate,
nitrilotrismethylene phosphonic acid or a mixture
thereof.

7. A gelatin product according to claim 6, wherein said gelatin product comprises a gelatin film, capsule, casing or coating.
8. A gelatin product according to claim 6, wherein said gelatin film, capsule, casing or coating comprises 0.1 to 10% by weight of at least one additive of the group consisting of urea, tryptophan, glutamic acid or nitrilotrismethylene phosphonic acid or mixtures thereof.
9. A pharmaceutical gelatin capsule shell prepared from compositions with improved stability for storage under hot and humid conditions and/or aldehydes comprising at least one additive selected from the group consisting essentially of ammonium sulfate, ammonium hydrogen sulfate, ammonium hydrogencarbonate, ammonium phosphate, ammonium hydrogenphosphate, ammonium dihydrogenphosphate, ammonium thiocyanate, sodium sulfate, sodium chloride, potassium sulfate, potassium chloride, lithium sulfate, lithium chloride, calcium sulfate, calcium chloride, magnesium sulfate, magnesium chloride, iron (II) sulfate, iron (II) chloride, iron (III) sulfate, iron (III) chloride, manganese (II) sulfate, manganese (II) chloride, glutamic acid, aspartic acid, asparagine, lysine, tryptophane, arginine, guanidine, urea, citric acid, ascorbic acid, ethylenediamine tetraacetate, nitrilotrismethylene phosphonic acid or a mixture thereof.
10. A pharmaceutical gelatin capsule shell containing 0.1 to 10% by weight of at least one additive of the group consisting essentially of ammonium sulfate, ammonium hydrogen sulfate, ammonium hydrogencarbonate, ammonium phosphate, ammonium hydrogenphosphate, ammonium dihydrogenphosphate, ammonium thiocyanate, sodium

sulfate, sodium chloride, potassium sulfate, potassium chloride, lithium sulfate, lithium chloride, calcium sulfate, calcium chloride, magnesium sulfate, magnesium chloride, iron (II) sulfate, iron (II) chloride, iron (III) sulfate, iron (III) chloride, manganese (II) sulfate, manganese (II) chloride, glutamic acid, aspartic acid, asparagine, lysine, tryptophane, arginine, guanidine, urea, citric acid, ascorbic acid, ethylenediamine tetraacetate, nitrilotrismethylene phosphonic acid or a mixture thereof. urea, tryptophan, glutamic acid or nitrilotrismethylene phosphonic acid or mixtures thereof.

11. A pharmaceutical gelatin capsule shell according to claim 10 containing 0.1 to 10% by weight of at least one additive of the group consisting essentially of urea, tryptophan, glutamic acid or nitrilotrismethylene phosphonic acid or mixtures thereof.

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09H 5/00, A61K 9/48	A3	(11) International Publication Number: WO 96/14365 (43) International Publication Date: 17 May 1996 (17.05.96)
(21) International Application Number: PCT/US95/13950 (22) International Filing Date: 31 October 1995 (31.10.95) (30) Priority Data: 08/334,974 7 November 1994 (07.11.94) US (71) Applicant: WARNER-LAMBERT COMPANY [US/US]; 201 Tabor Road, Morris Plains, NJ 07950 (US). (72) Inventors: CADE, Dominique; 11, rue des Americains, F-68000 Colmar (FR). MADIT, Nicolas; 51, avenue du Marechal-Juin, F-68100 Mulhouse (FR). (74) Agents: RYAN, M., Andrea; Warner-Lambert Company, 201 Tabor Road, Morris Plains, NJ 07950 (US) et al.		(81) Designated States: CA, CN, JP, KR, MX, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> (88) Date of publication of the international search report: 27 June 1996 (27.06.96)
(54) Title: PROCESS FOR STABILIZING GELATIN PRODUCTS (57) Abstract Process for the manufacturing of gelatin products with improved stability against storage under hot and humid conditions and/or aldehydes characterized in that at least one additive, preferred glutamic acid, tryptophan, or nitrilotrismethylene phosphonic acid or a mixture thereof is incorporated into the gelatin before forming the final product as usual as well as the gelatin compositions used and the products obtained by the process.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

INTERNATIONAL SEARCH REPORT

In: tional Application No
PCT/US 95/13950A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09H5/00 A61K9/48

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C09H A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CHEMICAL ABSTRACTS, vol. 100, no. 26, 25 June 1984 Columbus, Ohio, US; abstract no. 215551z, MORISHITA JINTAN 'Film compositions for preparation of soft capsules' page 346; see abstract & JP,A,59 039 834 ---	1-7,9-11
X	US,A,2 467 715 (THOMAS AUBREY WHITE) 19 April 1949 see column 2, line 1-37 ---	1-7
X	DD,A,225 426 (VEB JENAPHARM) 31 July 1985 see page 1, line 35 - line 37 ---	1-11
	-/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- 'A' document defining the general state of the art which is not considered to be of particular relevance
- 'E' earlier document but published on or after the international filing date
- 'L' document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- 'O' document referring to an oral disclosure, use, exhibition or other means
- 'P' document published prior to the international filing date but later than the priority date claimed

- 'T' later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- 'X' document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- 'Y' document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- '&' document member of the same patent family

Date of the actual completion of the international search

15 March 1996

Date of mailing of the international search report

24. 04. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Lensen, H

INTERNATIONAL SEARCH REPORT

In: tional Application No
PCT/US 95/13950

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR,A,2 617 047 (SANOFI) 30 December 1988 see page 2, line 6 - line 21 ---	1-11
A	DATABASE WPI Week 7821 Derwent Publications Ltd., London, GB; AN 37948A & SU,A,563 156 (VEG DRYING PRESERV) , 29 August 1977 see abstract -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Patent Application No

PCT/US 95/13950

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-2467715	19-04-49	NONE	
DD-A-225426		NONE	
FR-A-2617047	30-12-88	NONE	

Form PCT/ISA/210 (patent family annex) (July 1992)

THIS PAGE BLANK (USPTO)